

# A1 Garnet SUPER

## SPECIFICATIONS

GRADE #120

Mineralogy	Guaranteed (%)	Typical (%)
<b>Garnet</b>	Min - 90	92
<b>Chemical Analysis</b>		
Parameters		Typical (%)
<b>SiO<sub>2</sub></b>		35-38%
<b>Al<sub>2</sub>O<sub>3</sub></b>		20-24%
<b>Fe<sub>2</sub>O<sub>3</sub></b>		30-33%
<b>TiO<sub>2</sub></b>		1-1.5%
<b>CaO</b>		1-1.5%
<b>MgO</b>		6-9%
<b>ZrO<sub>2</sub></b>		Traces
<b>Soluble Chloride</b>		Less than 18 ppm
<b>Sieve Analysis</b>		
Mesh (US)		Retention (%)
<b>-100</b>		30-38
<b>+120</b>		41-45
<b>-120</b>		20-32
<b>Physical Analysis</b>		
<b>Specific Gravity</b>		4.1
<b>Hardness</b>		7 - 8.00 (Moh Scale)
<b>Bulk Density</b>		2.3 gm/cm <sup>3</sup>
<b>Conductivity</b>		< 10 Micron Siemens/Metre

**Note:** Garnet is a natural product and as such slight variations in the chemical analysis and size distribution should be expected. Special contracts covering guarantees other than those specified can be negotiated.

### Packaging

- 25 kgs. PE bags (max. 1000 kgs/ 1MT.)
- 1000 kgs. In 1MT Jumbo bag.

**Maxworth International Pty Ltd**

Level 1, 76-80 Turnham Avenue, Rosanna Victoria-3084, Australia  
 Tel: +61 3 9455 4400 | Fax : +61 3 9455 4433 | Email: enquiry@maxworthgroup.com.au